

## Barex® 210 Injection Grade

Barex Injection Grade resin is an impact modified acrylonitrile - methyl acrylate copolymer with excellent gas barrier and a wide range of chemical resistance. It can easily be used in injection molding, injection blow molding, and injection stretch blow molding of high barrier containers and chemically resistant parts.

### Typical Physical Properties

The physical properties of Barex 210 Injection Grade resin summarized in this brochure are typical, or average properties measured in accordance with standard test methods. The information is the best currently available. However, it is based on limited data and therefore subject to change without notice as new information becomes available.

### Typical Properties of Barex 210 Injection Grade

#### General

Density	72 lb/ft <sup>3</sup>	1.15 g/cm <sup>3</sup>	ASTM D792
Bulk Density	41 lb/ft <sup>3</sup>	0.66 g/cm <sup>3</sup>	ASTM D1895
Yield	24,080 in <sup>2</sup> -mil/lb	34.2 m <sup>2</sup> -25μm/kg	
Melt Index <sup>(1)</sup>	12 g/10 min	12 g/10 min	ASTM D1238
Mold Shrinkage	2-5x10 <sup>-3</sup> in/in	2-5x10 <sup>-3</sup> cm/cm	ASTM D955

#### Gas Permeability

Oxygen (73 °F, 100% RH)	0.8 cm <sup>3</sup> -mil/100 in <sup>2</sup> -24 hrs-atm	0.3 cm <sup>3</sup> -mm/m <sup>2</sup> -24 hrs-bar	ASTM D3985
Nitrogen (73 °F, 100% RH)	0.2 cm <sup>3</sup> -mil/100 in <sup>2</sup> -24 hrs-atm	0.08 cm <sup>3</sup> -mm/m <sup>2</sup> -24 hrs-bar	ASTM D3985
Carbon Dioxide (73 °F, 100% RH)	1.2 cm <sup>3</sup> -mil/100 in <sup>2</sup> -24 hrs-atm	0.45 cm <sup>3</sup> -mm/m <sup>2</sup> -24 hrs-bar	ASTM D3985
Water Vapor (100°F, 90%RH)	5.0 g-mil/100 in <sup>2</sup> -24 hrs-atm	2.0 g-mm/m <sup>2</sup> -24 hrs-bar	ASTM F1249-90

#### Mechanical

Tensile Strength, Yield	9,500 lb/in <sup>2</sup>	65.5 MPa	ASTM D638
Elongation, Yield	4%	4%	ASTM D638
Flexural Strength, Yield	14,000 lb/in <sup>2</sup>	96.5 MPa	ASTM D790
Flexural Modulus	480,000 lb/in <sup>2</sup>	3.31 GPa	ASTM D790
Izod Impact (Notched)	1.5 ft-lb/in	80.1 J/m	ASTM D256
Hardness, Rockwell	M60	M60	ASTM D785

#### Thermal

Heat Deflection Temperature	166°F (66 lb/in <sup>2</sup> ) 151°F (264 lb/in <sup>2</sup> )	74°C (455 KPa ) 66°C (1820 KPa )	ASTM D648
Thermal Conductivity	0.15 BTU/ft-hr-°F	0.25 W/m °K	ASTM C177
Specific Heat (20°C)	0.32 BTU/lb-°F	0.41 J/g-°C	ASTM C351
Linear Thermal Expansion (20-80°C)	3.7x10 <sup>-5</sup> in/in-°F	6.65x10 <sup>-5</sup> cm/cm-°C	ASTM D696

#### Optical (0.010" Thick Sheet)

Yellowness Index, P5-78 <sup>(2)</sup>	2.5	2.5
Haze, P5-78 <sup>(2)</sup>	2.7 %	2.7 %
60° Gloss, P24-76 <sup>(2)</sup>	120	120
Transmittance, P5-78 <sup>(2)</sup>	92.5 %	92.5 %

(1) 200 °C , 27.5 lbs., 0.0824"D x 0.3145"L (2) INEOS Test Method.



barex® resins

INEOS Barex

## Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an e-mail to: [info.barex@ineos.com](mailto:info.barex@ineos.com).

## Health and Safety Information

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained by calling 1-302-781-3128, or by sending an e-mail to: [info.barex@ineos.com](mailto:info.barex@ineos.com). Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

The Material Safety Data Sheet for this product contains shipping descriptions and should be consulted, before transportation, as a reference in determining the proper shipping description. If the material shipped by INEOS is altered or modified, different shipping descriptions may apply and the MSDS of the original material should not be used.

For additional information, samples, pricing and availability, please contact:

### INEOS Barex

261 Chapman Road  
Stockton Bldg - Suite 202  
Newark, DE 19702-5428  
USA  
Customer Service: +(1) 302-781-3128  
Fax: +(1) 302-266-0923  
email: [info.barex@ineos.com](mailto:info.barex@ineos.com)  
[www.ineosbarex.com](http://www.ineosbarex.com)

### For Sales in Europe

Velox GmbH  
Brandstwiete 1  
D-20457 Hamburg  
Germany  
Tel: +(49) (0) 40 36 96 88-0  
Fax: +(49) (0) 40 36 96 88 88  
email: [info@velox.com](mailto:info@velox.com)  
[www.velox.com](http://www.velox.com)

Technical information contained herein is furnished without charge or obligation, and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, INEOS makes no representation about, and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects or Industrial Hygiene requirements associated with particular uses of any product described herein. Nothing contained in this document shall be considered a recommendation for any use that may infringe patent rights, or an endorsement of any particular material, equipment, service, or other item not supplied by INEOS. The "Properties" and "Applications" listed in this document are not specifications. They are provided as information only and in no way modify, amend, enlarge, or create any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXCLUDED.

The name Barex is a trademark of INEOS USA LLC.